

# PRODUCT DATA SHEET

## ARCHCO 320 INORGANIC ZINC

### Two Part Inorganic Zinc

#### Description

Archco 320 Inorganic Zinc is an inorganic zinc primer for protection of steel. It has excellent performance in salt and heavy weathering environments.

#### Uses

Corrosion protection of steel structures, tanks and pipes in marine and industrial environments. The coating has good application properties and can be top coated.

#### Features

- Service temperatures up to 750°F (399°C)
- Long-term protection in corrosive environments
- Superior Abrasion Resistance
- Excellent salt spray resistance
- Low temperature/high humidity cure
- Application by conventional or airless spray
- Excellent resistance to fuels and organic solvents

#### Application

All contaminants shall be removed from the steel surface to be coated. Oil and grease should be removed in accordance to SSPC-SP-1. Surfaces shall be free from projections. Sharp edges, high points and fillets must be ground smooth including all corners. Prepare surfaces by grit blasting to a clean white finish, SSPC-SP 5-63 or Sa 3. Maximum product performance will be achieved by blasting with 16-40 mesh silica sand, G-50 steel grit or equivalent material to obtain a 1-1/2 mil (38 microns) angular profile.

Archco 320 can be sprayed by conventional or airless spray. Mix Part A (liquid) thoroughly then add Part B (dust). Mix thoroughly with mechanical agitation while adding Part B (dust). Do not mix in reverse. Mix until free of any lumps, then pour mixture through a 30 mesh screen. The coating shall be applied with a single pass with a 50% overlap holding the gun 10-12 inches (254 - 305 mm) from surface at a parallel right angle. The coating thickness should be measured using a wet film thickness gauge. Clean up equipment with Xylene or equivalent solvent.

#### FOR AIRLESS SPRAY

Use 3/8" ID material hose  
Fluid Pump Ratio min. 45:1  
Fluid Orifice, Inches .025"-.031" (0.6 mm - 0.78 mm)  
Approx. Fluid Pressure 1500-2000 psi (10.3 MPa - 13.7 MPa)

#### FOR CONVENTIONAL SPRAY

Binks #18  
Fluid Tip 66  
Fluid Needle 65  
Air Cap 66PA  
Air to gun 60 to 70 psi (0.41 MPa - 0.48 MPa)  
Air to pot 10 to 12 psi (0.07 MPa - 0.08 MPa)  
Pot should be equipped with agitator



# Archco 320 Inorganic Zinc

## PROPERTY SPECIFICATIONS

PROPERTIES	VALUE
Solids Content (+/- 2%)	68%
Minimum Temperature & Humidity	Do not apply below 50°F (10°C) & above 85% humidity
Operating Temperature	
Immersed	Consult Denso representative regarding application
Atmospheric	750°F (399°C)
Percent of zinc in dried film by weight	78%
Dry Film Thickness	2.5 mils to 6 mils (63.5 to 152 microns)
Number of coats	One
Theoretical Coverage at 3 to 6 mils	436 - 182 SF/Gal
Thinning required	10 to 15% with Xylene
Shelf Life @ 41°F (5°C) to 110°F (43°C)	1 year
Flash Point	77°F (25°C)
Pot Life	
@ 77°F (25°C)	12 hours
Dry to Touch	
@ 77°F (25°C)	15 - 30 minutes
Dry to Handle	
@ 77°F (25°C)	8 - 12 hours
Topcoat Time	
@ 77°F (25°C)	12 - 16 hours
Thinner	10-15% with Xylene
Ratio by volume (A to B)	10 Parts A to 14.3 Parts B
Performance Data	
Oil Immersion (ASTM D-1308)	Passes 1000 hours
Salt Water Immersion (ASTM D-1308)	Passes 1000 hours
Slip Co-Efficient (ASTM A-328)	Meets Class B rating
Pencil Hardness (ASTM D-3363)	H
Adhesion (ASTM D-4541)	600 psi (4 MPa)
Salt Fog Resistance (ASTM (B-117)	Passes 1000 hours
Weight solids % (ASTM D-2369)	76%
Color	Green

**STORAGE:** Store in containers in a dry well ventilated area. The containers should be kept tightly sealed. Shelf Life: 6 months when stored between 41°F – 110°F (5°C-43°C).

**CLEANING:** Clean equipment with Xylene or equivalent solvent cleaner.

**HEALTH AND SAFETY:** Wear protective clothing and ensure adequate ventilation. Avoid contact with skin and eyes. See material safety data sheets for further information.

**PACKAGING:** 1.5 and 5 gallon (5.7 L and 19 L) kits



### DENSO NORTH AMERICA

**HOUSTON:**  
9747 Whithorn Drive,  
Houston, Texas,  
U.S.A. 77095  
Tel: 281-821-3355  
Fax: 281-821-0304

**TORONTO:**  
90 Ironside Crescent,  
Unit 12, Toronto,  
Ontario, Canada M1X1M3  
Tel: 416-291-3435  
Fax: 416-291-0898

[www.densona.com](http://www.densona.com)

*A Member of Winn & Coales International*

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.