

ARCHCO 420 EPOXY

Low Permeability, MIC Resistance & Acid-Resistant Protective Lining

Description

Archco 420 is a two-part, high solids, modified epoxy lining provide ultra-low permeability. It has excellent resistance to microbial-induced corrosion (MIC) and acids. Archco 420 is suitable for application via single-leg or plural spray equipment.

Uses

Archco 420 provides a protective lining for storage tanks and pipelines with ultra-low permeability. The coating will provide excellent protection against MIC and acidic environments. It is also resistant to hydrocarbons where MIC is found.

Features

- Ultra-low permeability/transmission
- Excellent resistance to MIC
- Resistant to hydrocarbons
- Excellent acid resistance
- Long working life
- Good cure response

Application

All contaminants shall be removed from the steel surface to be coated. Oil and grease should be removed in accordance to SSPC-SP-1. Surfaces shall be free from projections. Sharp edges, high points and fillets must be ground smooth including all corners. Prepare surfaces by grit blasting to a clean, near-white finish, per SSPC-SP 10, NACE No. 2 or Sa 2-1/2. Appropriate angular grit shall be used to achieve a 3-5 mil (76 to 127 microns) anchor profile. Remove grit prior to coating.

To spray Archco 420 in a plural-component system, an airless spray unit with a proportioning pump capable of a volume mixing ratio of 4:1 shall be used. Standard ancillary equipment should include minimum 10 gallon (38 L) hoppers, 2 each static mixers, 25 ft. (7.6 m) max x 1/4" (6.35 mm), and mastic gun with a 19 to 25 thou (0.48 - 0.63mm) tip. A minimum of 2800 psi (19 MPa) fluid pressure at the tip is required for proper atomization. Part A should be heated to 80°F-100°F (27°C-38°C) and Part B should be heated to 80°F-100°F (27°C-38°C). Hose bundle shall be set at 80°F-100°F (27°C-38°C). A single-leg, airless spray unit may also be used. The unit shall have a minimum of 45:1 airless pump. When using the airless unit, the Archco 420 should not be thinned more than 5% with Archco 400E Thinner (3 lbs /1.4 kg per 5 gal /19 L kit). Material shall be between 70°F and 90°F (21°C-32°C).

A wet-on-wet spray technique should be used to achieve a thickness of 12-15 mils (305 - 381microns) WFT. The coating thickness should be measured using a wet-film thickness gauge. The equipment settings are only guidelines and may vary based on equipment and specific application.



Archco 420 Epoxy

TECHNICAL DATA

PROPERTIES	VALUE
Solids Content	79%
Base Component – unmixed @ 77°F (25°C)	
Specific Gravity	1.7
Viscosity	30,000 cP
Color	Light Blue
Hardener – unmixed @ 77°F (25°C)	
Specific Gravity	1.5
Viscosity	1,000 cP
Color	Amber
Mixed Material – mixed @ 77°F (25°C)	
Specific Gravity	1.6
Viscosity	10,000 cP
Color	Light Blue
Mixing Ratio (A/B) by Volume	1:1
by Weight	1.2:1
Cure Times	
Pot Life @ 77°F (25°C)	240 minutes
Pot Life @ 97°F (36°C)	100 minutes
Time to Dry @ 35°F (2°C)	10-12 hours
Time to Dry @ 50°F (10°C)	3-5 hours
Time to Dry @ 77°F (25°C)	3-4 hours
Recoat Window	
@ 77°F (25°C)	Overnight
Theoretical Coverage	80 ft ² /15 mils/gallon (2.1 m ² /381 microns/Liter)
Thickness per coat	8-12 mils DFT (203-305 microns)
Holiday Detection – based on min. mil.	125 volts/mil (4920 volts/mm)
Hardness (ASTM D2240-02)	Shore D 80
Adhesion to Steel	2,200 psi (15.2 MPa)
Application Temperature	20°F-100°F (-7°C-36°C)
Application Temperature – Metal	60°F-100°F (15°C-38°C)
Application Temperature – Material	70°F-90°F (21°C-32°C)
Service Temperature	0°F-200°F (-18°C-93°C)

STORAGE: Minimum 24 months when stored in original container @ 40°F (4°C) to 105°F (41°C). On job site where temperatures are below 50°F (10°C), product should be kept warm to allow for easy transfer into storage hoppers for warming to proper spraying temperatures.

CLEANING: Clean equipment with isopropyl alcohol, butanol, or equivalent solvent cleaner.

HEALTH AND SAFETY: Wear protective clothing and ensure adequate ventilation. Avoid contact with skin and eyes. See Safety Data Sheet for further information.

PACKAGING: 5 Gallon (19 liters) and 10 gallon (38 liters) kits. Other sizes available upon request.



DENSO NORTH AMERICA

HOUSTON:
9747 Whithorn Drive,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.