

# PRODUCT DATA SHEET

## ARCHCO 453HT PLURAL

### Heat Resistant Coating - Plural

#### Description

Archco 453 HT is an ultra-high solids, fast curing, technologically advanced epoxy-phenolic novolac lining. It is specifically designed to handle the harsh environments in the petroleum industry, including all petroleum crudes. It is an excellent internal lining to use in Free Water Knockouts, Treaters, Separators, and tanks with high operating temperatures. It combines excellent heat resistance with outstanding corrosion protection. Archco 453 HT resists immersion temperatures up to 325°F (163°C) for many applications and higher temperatures in non-immersion service.

#### Uses

Steel or concrete of any size in the petroleum industry, including petroleum bulk storage tanks, downhole tubular pipes, downhole casing exteriors, interior and exterior pipes, floors, tank pads, trenches, troughs, sumps and pits.

#### Features

- Excellent adhesion
- High temperature stability
- Abrasion and impact resistance
- High temperature water resistances, oil & gas
- Thermal and mechanical shock resistance
- Excellent flexibility
- Resists wide range of chemicals, produced water, sea water

#### Application

All surfaces must be clean and dry, free of dust, dirt, oil or other foreign matter. Steel surfaces shall be abrasive blasted to SSPC 10 near white finish with a minimum of 3-5 mil (76-127 microns) angular profile for best results. Concrete shall be abrasive blasted or etched with 10% muriatic acid. Use of a primer is required for concrete to improve adhesion and minimize outgassing. See a Denso representative for additional information.

Plural component equipment is recommended for application. Under controlled conditions, single-leg airless equipment may be used. For plural spray application, utilize a pump with a 4:1 mix ratio (GRACO 68:1 or greater power ratio is recommended). Also needed are (2) 3/8" (0.009 mm) inside diameter x 12" (305 mm) long elemental static mixers which are available from Graco. Heated tanks and heated lines up to 150°F (66°C) may be necessary. The resin fluid line should be 1/2" (0.13 mm) ID minimum (recommended), the hardener fluid line should be 3/8" (9.5 mm) ID minimum (recommended), and the high pressure solvent fluid line should be 1/4" (6.3 mm) minimum (recommended). A reversible tip (0.029"-0.035" / 0.74 - 0.89 mm) is suggested. Keep in mind that plural component application requires volumetric check of the mix ratio (utilizing a ratio monitoring system) before and during the application process. Any variation in product color during application will indicate the plural pump is off-ratio. Archco "Spray Application Guidelines" are available upon request.

For heavily pitted or porous steel, the spray-roll-spray technique is recommended. Spray-apply approximately 50% of the required film thickness followed immediately with a short-nap roller or squeegee to work material into bottom of pitted areas. Follow the rolled or squeegee application with a spray application of the product to the remainder of the required film thickness. We recommend thinning the material with 2% Archco 400E Thinner to facilitate in this type of application. Thinning reduces handing qualities of the lining and will slow curing. For plural equipment, proportion thinner between resin and hardener according to 4:1 mix ratio. For plural application, viscosity of the resin and hardener varies with temperature. For best results, heat the resin side to a maximum of 140°F (60°C) and heat the hardener side to a maximum of 110°F (43°C). Keep in mind that at elevated temperatures the gel time will be faster. It is important to understand that this is a single coat, continuous application procedure.

Consult Denso representative for more information.



# Archco 453HT Plural

## TECHNICAL DATA

### PROPERTIES

### VALUE

<b>Solids Content by Volume</b>	98 - 100%
<b>Minimum Dewpoint / Substrate Differential</b>	Dewpoint +5°F (+3°C)
<b>Minimum Substrate Temperature</b>	60°F (16°C)
<b>Minimum Ambient Temperature</b>	60°F (16°C)
<b>Mixing Ratio (A/B) by Volume</b>	4:1
<b>Recommended Thickness</b>	20 - 40 mils DFT (508 - 1016 microns DFT)
<b>Theoretical Coverage</b>	
@ 1 mil (0.02 mm) dry	1604 sq. ft. per gallon (39.4 sq. m. per liter)
@ 20 mil (0.50 mm) dry	80 sq. ft. per gallon (2.0 sq. m. per liter)
@ 40 mil (1.02 mm) dry	40 sq. ft. per gallon (1.0 sq. m. per liter)
<b>Minimum Dry Time @ 77°F (25°C) &amp; 50% Relative Humidity (ASTM D 1640)</b>	
To Touch	1 Hour
To Handle	2 - 3 Hours
To Recoat	3 Hours
Maximum Recoat Time	6 Hours
<b>Cure for Immersion (Shore D 75 - 80) @ 77°F (25°C)</b>	12 hours
<b>Flash Point</b>	>200°F (93°C)
<b>Hardness</b>	(Shore D min.): 80
<b>Temperature Resistance*</b>	
Dry Heat	400°F (204°C)
Short Term	700°F (371°C)
<b>Pot Life @ 72°F (22.2°C)</b>	30 mins.
<b>Color</b>	Tan
<b>VOC</b>	0.12 lbs/gal (14 g/l)

\*Note: Continuous immersion temperature resistance is dependent on particular reagent exposure. Consult a Denso representative.

**STORAGE:** Minimum 24 months when stored in original containers @ 65°F (18°C) to 85°F (30°C).

**CLEANING:** Clean equipment with MEK or equivalent solvent cleaner, such as Archco 400E Thinner.

**HEALTH AND SAFETY:** Wear protective clothing and ensure adequate ventilation. Avoid contact with skin and eyes. See material safety data sheet for further information.

**PACKAGING:** 25 gallon (95 liters) kit. Other kit sizes available upon request.

Dispensing guns and static mixing tips (50 ml or 375 ml) sold separately.



**DENSO NORTH AMERICA**

**HOUSTON:**  
9747 Whithorn Drive,  
Houston, Texas,  
U.S.A. 77095  
Tel: 281-821-3355  
Fax: 281-821-0304

**TORONTO:**  
90 Ironside Crescent,  
Unit 12, Toronto,  
Ontario, Canada M1X1M3  
Tel: 416-291-3435  
Fax: 416-291-0898

[www.densona.com](http://www.densona.com)

**A Member of Winn & Coales International**

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.