

DENSO BUTYL 33 TAPE

Butyl Rubber Adhesive/Sealant Tape

Description

Denso Butyl 33 Tape is a smooth, gum-like material layered between two release liners. Available in gray rolls.

Uses

For the joining and sealing together of a variety of surfaces including polyethylene, polypropylene, PVC, concrete, metal and wood.

Features

- Immediate leakproof results
- Excellent adhesion
- Aggressive grip
- Stays flexible
- Excellent conformability and consistent uniform thickness
- Easy and fast application
- No harmful VOC's
- Free of asphalt and solvent

Application

Prepare surfaces by removing dust, dirt, grease, etc. Peel off CLEAR release liner (apply exact the first time, trying to remove may damage tape). Do not stretch. Press down firmly starting at center and working toward outside edge of tape, removing any bubbles. Edges must have no openings, tunnels or fishmouths. Remove WHITE release liner. Lineup surfaces to be joined and carefully press the surfaces together.

Denso[®]



Denso Butyl 33 Tape

Property Specifications

PROPERTIES	ENGLISH
Tensile Strength	285 PSI
Peel Strength	17 lbs. per linear in.
Bonding Time	Immediate (full bond within 24 hours)
Elongation at Break (ASTM D1000)	560%
Dielectrical Strength (ASTM D1000)	30 kV
Water Vapor Transmission (ASTM E96)	< 1 g/ft ² /24 hour
Water Absorption (ASTM D570)	< 0.15%
Resistance to Hydrocarbons	Good
Resistance to Acids, Alkalis and Salts	Excellent
Temperature Range	
For Application	35°F to 110°F
For Continuous Service	-20°F to 200°F
Dimensions	
Roll Length	50 feet
Width	2", 4", 6"
Thickness (ASTM D1000)	33 mil
Color	Gray

Quantity Estimates

Roll Width	Roll Length	Rolls/ Case
2"	50'	24
4"	50'	12
6"	50'	8

Other roll widths are available on request.



DENSO NORTH AMERICA

HOUSTON:
9747 Whithorn Drive,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.