

# PROTAL 7200 CARTRIDGE (1000 ml)

**Fast Cure, High Build Spray Applied Pipeline Coating**

## Description

Protal 7200 Cartridge (1000 ml) is a VOC free, 100% solids, 2 part epoxy coating specially formulated to compliment FBE coated pipe. It is a high build liquid coating that is spray applied in one coat in the field or shop. It cures very fast to allow quick handling and backfill times.

## Uses

On-site protection of girth welds, tie-ins, welds for boring applications, repairs to FBE, push-rack applications, station piping, fittings and fabrication. Also used for main line pipe coating, sacrificial coating for directional drill and road bore pipe, and rehabilitation of existing pipelines.

## Features

- Excellent adhesion (compliments FBE coated pipe)
- Fast cure
- High build (up to 60 mils / 1524 microns in one coat)
- High abrasion resistance for drilling applications
- Can be used as an abrasion resistant coating (ARO)
- Does not shield cathodic protection
- CSA Z 245.30-14 compliant

## Application

**Spray:** Prepare surfaces by grit blasting to a clean near white finish, SSC-SP 10/ NACE No. 2. Heat and check temperature of Part "A" Protal Repair Cartridge to approximately 120°F to 135°F (49°C to 54°C) in a microwave. Convection oven, weld box or other methods (do not overheat and check with a infrared gun). Utilize the Protal Air Cartridge Gun to spray product. A wet on wet spray technique should be used to achieve a minimum thickness of 20 mils (508 microns). The coating thickness should be measured using a wet film thickness gauge.

For complete application instructions please refer to Protal 7200 Air Cartridge Gun Application Specifications.



# Protal 7200 Cartridge (1000 ml)

## TECHNICAL DATA

### PROPERTIES

### VALUE

<b>Solids Content</b>	100%
<b>Mixed Material - (Mixed) @ 77°F (25°C)</b>	
Specific Gravity	1.63
Viscosity	170,000 cps
Color	Green
<b>Mixing Ratio (A/B) by Volume</b>	3 Parts Base: 1 Part Hardener
<b>Cure Times</b>	
Pot Life @ 77°F (25°C)	14 - 17 Minutes
Pot Life @ 97°F (36°C)	7 - 8 Minutes
Handling Time @ 77°F (25°C)	2.5 - 3 Hours
Handling Time @ 117°F (47°C)	1 Hour
Handling Time @ 157°F (69°C)	20 Minutes
<b>Recoat Window</b>	
@ 57°F (14°C)	5 Hours
@ 77°F (25°C)	2 Hours
@ 97°F (36°C)	1 Hour
<b>Theoretical Coverage</b>	14 ft <sup>2</sup> /30 mils/liter (1.301 m <sup>2</sup> /762 microns/L)
<b>Thickness - Weld Joints / FBE Repairs</b>	
Minimum/Maximum	20/70 mils (508/1778 microns)
Recommended	25 - 30 mils (635 - 762 microns)
<b>Thickness - Bore Pipe</b>	
Minimum/Maximum	40/70 mils (1016/1778 microns)
Recommended	45 - 60 mils (1143 - 1524 microns)
<b>Holiday Detection</b>	125 volts/mil (4,920 V/mm)
<b>Cathodic Disbondment Test (ASTM G95)</b>	
28 Days @ 77°F (25°C)	3 mm
28 Days @ 150°F (65°C)	4 mm
28 Days @ 185°F (85°C)	6 mm
28 Days @ 203°F (95°C)	6 mm
<b>Hardness (ASTM D-2240-02)</b>	Shore D 85 +/-2
<b>Impact Resistance (ASTM G14-04) @ 32°F (0°C)</b>	70.6 in-lbs.
<b>Tabor Abrasion (ASTM 4060-07)</b>	
-1000 cycles, CS-17 wheels, 1000 g. load	1,270 cycles per mil
<b>Gouge Resistance (Partech Test - 40 kg load)</b>	15.4 mils (391 microns)
<b>Dielectric Strength (ASTM D-149)</b>	450 V/mil (17,716 V/mm)
<b>Adhesion to Steel (ASTM D-4541-02)</b>	3,956 psi (27.3 MPa)
<b>Adhesion to FBE (ASTM D-4541-02)</b>	2,579 psi (17.8 MPa)
<b>Service Temperature</b>	-40°F to 203°F (-40°C to 95°C)
<b>Application Temperature</b>	-30°F to 212°F (-34°C to 100°C)

Note: If temperature falls below 50°F (10°C), surface must be preheated and maintained throughout the cure process.

**STORAGE:** Minimum 24 months when stored in original containers @ 40°F (4°C) to 105°F (41°C). On job site where temperatures are below 50°F (10°C) product should be kept warm to mix properly (65°F to 85°F optimal).

**CLEANING:** Clean equipment with MEK or equivalent solvent cleaner.

**HEALTH AND SAFETY:** Apply under well ventilated conditions. Wear suitable protective clothing and glasses. See material safety data sheets.

**PACKAGING:** 1000 ml dual cartridges. (9 per carton).

Dispensing guns and static mixing tips (1000 ml) sold separately.



### DENSO NORTH AMERICA

#### HOUSTON:

9747 Whithorn Drive,  
Houston, Texas,  
U.S.A. 77095  
Tel: 281-821-3355  
Fax: 281-821-0304

#### TORONTO:

90 Ironside Crescent,  
Unit 12, Toronto,  
Ontario, Canada M1X1M3  
Tel: 416-291-3435  
Fax: 416-291-0898

[www.densona.com](http://www.densona.com)

*A Member of Winn & Coales International*

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.