

# PROTAL 7900HT

## High Temperature Pipeline Coating

### Description

Protal 7900HT is a VOC free, 100% solids epoxy coating for pipelines operating at higher temperatures. It is a high build liquid coating that can be hand or spray applied in one coat in the field or shop. It cures fast to allow quick backfill when applied to hot pipe.

### Uses

Spray or hand applied to pipelines operating at elevated temperatures. Used on girth welds, pipe, fittings, valves and fabrication.

### Features

- High build (up to 40 mils / 1016 microns in one coat)
- Can be hand or spray applied
- Excellent adhesion
- Intermittent service temperature up to 300°F (150°C)
- Very low permeability
- High abrasion resistance
- Safe and environmentally responsible
- Does not shield cathodic protection

### Application

**Brush:** Prepare surfaces by grit blasting to a clean near white finish, SSC-SP 10/ NACE No. 2. Appropriate angular grit shall be used to achieve a 2.5 to 5 mil (0.063 - 0.125 mm) anchor profile. Initially stir the base and hardener. Add the hardener to base and mix at a slow speed until a constant color is achieved making sure all sides of container are scraped. Pour mixed material onto surface and brush, trowel or roll to required mil thickness. A wet film thickness gauge shall be used to measure mil thickness. If surface temperature falls below 50°F (10°C), surface should be preheated to achieve faster cure. Preheat may be achieved with a propane torch or induction coil. Resin and hardener component shall be kept warm, at a minimum of 60°F (15°C), to mix easily. Product can be applied to surfaces ranging from 40°F (4°C) to 220°F (105°C) at a minimum of 30 mils. Immediately pour mixed material onto surface and brush, trowel or roll to required mil thickness. A wet film thickness gauge should be used to measure mil thickness.

**Spray:** Prepare surfaces by grit blasting to a clean near-white finish, SSPC-SP 10/ NACE No. 2. The equipment should be a plural component airless spray unit with a proportioning pump capable of a volume mixing ratio of 3:1. Standard ancillary equipment should include minimum 10 gallon (37.85 liter) hoppers, 2 ea. static mixers, 25 ft. (7.3 m) max x 1/4" (0.64 cm) whip hose, and mastic gun with a 19 to 27 thou tip. (Applicator should consult with Denso regarding recommended equipment). Part A should be heated to 115°F -135°F (46°C - 57°C) and Part B heated to 110°F -130°F (43°C - 55°C). Hose bundle shall be set at 120°F -135°F (49°C - 57°C). A wet-on-wet spray technique should be used to achieve a minimum thickness of 25 mils (635 microns). The coating thickness should be measured using a wet-film thickness gauge. The equipment settings are only guidelines and may vary based on equipment.

For complete application instructions please refer to Protal 7900HT application specifications.



# Protal 7900HT

## TECHNICAL DATA

PROPERTIES	VALUE
<b>Solids Content</b>	100%
<b>Base Component – unmixed @ 77°F (25°C)</b>	
Specific Gravity	1.54
Viscosity	43,000 cps
Color	White
<b>Hardener – unmixed @ 77°F (25°C)</b>	
Specific Gravity	1.43
Viscosity	27,800 cps
Color	Black
<b>Mixed Material – mixed @ 77°F (25°C)</b>	
Specific Gravity	1.51
Viscosity	70,800 cps
Color	Gray
<b>Mixing Ratio (A/B) by Volume</b>	3 Parts Base: 1 Part Hardener
<b>Pot Life @ 77°F (25°C)</b>	30 minutes
<b>@ 97°F (36°C)</b>	15 minutes
<b>Theoretical Coverage</b>	14 ft <sup>2</sup> /30 mils/liter (1.3 m <sup>2</sup> /762 microns/liter)
<b>Actual Coverage</b>	8 - 10 sq. ft./liter (0.7 m <sup>2</sup> - 0.9 m <sup>2</sup> /liter)
<b>Thickness</b>	
Minimum/Maximum	25/60 mils (635/1524 microns)
<b>Holiday Detection</b>	125 volts/mil (4,920 V/mm)
<b>Cathodic Disbondment Test (ASTM G95)</b>	
28 Days @ 176°F (80°C)	5.25 mm
28 Days @ 250°F (120°C)	8.1 mm
28 Days @ 302°F (150°C)	8.8 mm
<b>Resistance to Cathodic Disbondment</b>	Excellent
<b>Abrasion Resistance</b>	Excellent
<b>Adhesion to Steel</b>	3,030 psi (21 MPa)
<b>Continuous Maximum Service Temperature</b>	250°F (121°C)
<b>Intermittent Maximum Service Temperature</b>	300°F (150°C)
<b>Hardness (ASTM 2240)</b>	Shore D min. 80-85
<b>Initial Handling @ 77°F (25°C)</b>	4 to 6 hours
<b>Initial Handling @ 220°F (104°C)</b>	15 to 20 minutes

**STORAGE:** Minimum 24 months when stored in original containers between 40°F (4°C) and 100°F (38°C). On job-site where temperatures are below 68°F (20°C) product must be kept warm to mix properly.

**CLEANING:** Clean equipment with MEK or equivalent solvent cleaner.

**HEALTH AND SAFETY:** Wear protective clothing and ensure adequate ventilation. Avoid contact with skin and eyes. See material safety data sheets for further information.

**PACKAGING:** 1, 2, 75 and 800 liter kits



### DENSO NORTH AMERICA

**HOUSTON:**  
9747 Whithorn Drive,  
Houston, Texas,  
U.S.A. 77095  
Tel: 281-821-3355  
Fax: 281-821-0304

**TORONTO:**  
90 Ironside Crescent,  
Unit 12, Toronto,  
Ontario, Canada M1X1M3  
Tel: 416-291-3435  
Fax: 416-291-0898

[www.densona.com](http://www.densona.com)

*A Member of Winn & Coales International*

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.