

# DENSO HOTLINE TAPE

## High Temperature Petrolatum Tape

### Description

Denso Hotline Tape is composed of a synthetic fabric impregnated with a special blend of high temperature petrolatum, mineral fillers and a clear polyethylene backing.

### Uses

A specifically developed tape for use in high temperature applications. Ideal for pipe work above or below ground, underneath pipe insulation or for pipes laid in concrete. Adhesion is increased when applied to surfaces above 90°F (32°C).

### Features

- Service temperature up to 230°F for above ground (180°F for below ground)
- Applied to marginally prepared surfaces (SSPC SP 2-3)
- UV resistant
- Resistant to water, acid, salts & soil organics
- Encapsulation of lead paint
- Contains no solvents
- Easy applications from arctic to tropical temperatures
- Ready for immediate service after application
- No primer is required

### Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi is also suitable. Spirally wrap the tape with a minimum 1" overlap. For severely corrosive environments, a 55% overlap is recommended. While wrapping, press air pockets out and smooth all lap seams. Where tape rolls need to be joined, ensure that the overlap is sufficient between rolls to provide continuous protection. For below ground applications, an approved Denso outerwrap is recommended.

Irregular surfaces such as valves, flanges, etc. may require the use of Densyl Mastic or Denso Profiling Mastic. Refer to the product sheets for these specific products for information on application and selection.



# Denso Hotline Tape

## Property Specifications

PROPERTIES	ENGLISH	METRIC
Thickness (ASTM D1000)	46 mils	1.15 mm avg.
Weight	.295 lbs/ft <sup>2</sup>	1.44 kg/m <sup>2</sup> avg.
Breaking Strength (ASTM 1000)	22.5 lbf/in. min.	200 N/50 mm min.
Elongation @ Break	15%	15%
Breakdown Voltage (55% overlap)	16 kV min.	16 kV min.
Resistance to Cathodic Disbonding (ASTM G-8 30 Days Group B)	.31 in <sup>2</sup> avg.	200 mm <sup>2</sup> avg.
Maximum Service Temperature		
Above Ground	230°F	110°C
Below Ground	180°F	83°C
Roll Width	2" to 12"	50 to 300 mm
Roll Length	33 ft	10 m
Recommended Primer	No Primer Required	

## Quantity Estimates

Tape Width	Rolls*/Case	Coverage with 1" Overlap	Coverage with 55% Overlap
2"	36	87 ft <sup>2</sup> /case	87 ft <sup>2</sup> /case
4"	18	145 ft <sup>2</sup> /case	87 ft <sup>2</sup> /case
6"	12	162 ft <sup>2</sup> /case	87 ft <sup>2</sup> /case
8"	8	150 ft <sup>2</sup> /case	77 ft <sup>2</sup> /case
12"	6	177 ft <sup>2</sup> /case	87 ft <sup>2</sup> /case

\* All rolls are 33 feet in length.



**DENSO NORTH AMERICA**

**HOUSTON:**  
9747 Whithorn Drive,  
Houston, Texas,  
U.S.A. 77095  
Tel: 281-821-3355  
Fax: 281-821-0304

**TORONTO:**  
90 Ironside Crescent,  
Unit 12, Toronto,  
Ontario, Canada M1X1M3  
Tel: 416-291-3435  
Fax: 416-291-0898

www.densona.com

**A Member of Winn & Coales International**

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.